Appender Col Psyn

SPEED POST

PHONES: 2451759-78

GRAM : LABDEY

No. Tex/1101/D/TEX-1/CPSG

GOVERNMENT OF INDIA MINISTRY OF

DEFENCE

5-385 DMRDIN DEFENCE RESEARCH & DEVELOPMENT

ORGANISATION

TELEX : 325-385 DMRDIN FAX : 0512-2450404

: 0512-2404774

E-MAIL: : dmsrde@sanchar.net.in

DEFENCE MATERIALS & STORES RESEARCH

& DEVELOPMENT ESTABLISHMENT DMSRDE P. O. G. T. ROAD KANPUR-208013

All correspondence to be addressed to the Director and this Establishment reference he quoted invariably while replying



DATED:

February 8, 2008

To.

The Directorate General
CRPF (Proc Cell. Prov. Directorate)
Block No.1, CGO Complex
Lodhi Road
NEW DELHI -110003

SUB:-

SPECIFICATION FOR A.K.47 RIFLE* SLING(NYLON) AND CARBINE SLING (NYLON)

REF:-

Our letter No. F - 1/LED-W Tex dt 08 Jan 2008.

Specification of metal components of subject store has been forwarded to you vide our letter cited above. Further, on going through the specification of subject store forwarded to you vide our letter No. D/1315/Tex-1 dt. 01.Sep.2004, it was observed that some amendment in that specification was required. So the necessary amendments have been made and the fresh copy of the same(only Textile component) is forwarded to you for further necessary action at your end.

Encls.: Copy of Specification (Ten Pages)

CRPF (

Sc. 'D'

FOR DIRECTOR

CISF

ITBP 201

SSB

10 Boundary

NSG/

1

A/Rifl

BRP&D

DA Tout

CE RESEARCE

OTORES RESEAR



 $c\theta$



SPECIFICATION OF NYLON SLING FOR AK-47RIFLE & CARBINE

Mhe BSF

CISE

ITBP

SSB NSG

A/Rifle

BBP&D



GOVERNMENT OF INDIA (MINISTRY OF DEFENCE)

Provisional Specification No. DMSRDE/T&GS/2004/01/CPSG

SPECIFICATION FOR NYLON SLING FOR . AK-47 RIFLE & CARBINE

- THIS SPECIFICATION CONSISTS OF TEN PAGES
- 2. THIS SPECIFICATION IS INTENDED TO GUIDE PURCHASE MANUFACTURE OF WEB SLINGS, FOR AK-47 RIFLE AND CARBINE FOR CRPF REQUIREMENT.
- 3. THIS SPECIFICATION OR ANY DRAWING PATTERN OR ANY OTHER INFORMATION ISSUED IN CONNECTION THEREWITH MAY ONLY BE USED FOR SPECIFIC ORDER PLACED BY A COMPETENT AUTHORITY IT IS NOT TO BE USED FOR ANY OTHER PURPOSE WHAT SO EVER WITHOUT THE EXPRESS WRITTEN SANCTION OF APPROPRIATE AUTHORITY.
- 4. ALL CLAUSES IN THIS SPECIFICATION SHALL BE COMPLIED WITH IN EVERY RESPECT IRRESPECTIVE OF SOURCE OF SUPPLY OF THE MATERIAL AND OR COMPONENTS.
- 5. IN CASE OF ANY DISCREPANCY BETWEEN THIS SPECIFICATION AND ANY SAMPLE OR PATTERN, LOANED FOR ANY PURPOSE, THIS SPECIFICATION AND OR OTHER CONNECTED SPECEFICATIONS OR SHALL BE TAKEN AS CORRECT AT THE TIME OF DRAWINGS FINALISATION OF A CONTRACT.
- 6. WHENEVER A REFERENCE TO ANY OTHER SPECIFICATION DRAWING OCCURS IN THIS SPECIFICATION, IT SHALL BE TAKEN AS REFERENCE TO THE LATEST VERSION OF THAT SPECIFICATION/ DRAWING EXISTING AT THE TIME OF FINALISATION OF A CONTRACT.


ISSUED BY THE DIRECTOR

DEFENCE MATERIALS & STORES

RESEARCH & DEVELOPMENT ESTABLISHMENT

DMSRDE POST OFFICE

KANBUR-208 0438



1. SCOPE

1.1 This specification covers the requirements of Nylon Webbing/Tapes used as a sling (Textile Component) used as a sling for AK-47 Rifle and Carbine.

2. RELATED SPECIFICATION AND AVAILABILITY.

2.1 Indian standard specifications are obtained on payment from the secretary (Administration), B.S. Manak Bhawan, 9 Bhadur Shah Zafer Marg. New Delhithor from their region of branch offices.

3. SEALED SAMPLE

3.1 The sealed samples held in the custody of the AHSP shall constitute the standard of particulars not defined in this specification.

4. MATERIALS.

- 4.1 Multifilament nylon yarn having approximate tenscity and denier as per clause 6.1 with nominal twist shall be used in the manufacture of web and tapes so as to achieve the various requirements as stipulated in clause 6.
- 4.2 In place of nietal components shown in attached plates No. 1,2,3 & 4 of this specification, refer specification No.DMSRDE/ES&S/(LED)/2007/229
- 5. MANUFACTURE, WORKMANSHIP AND FINISH .
- 5.1 The Web and Tapes shall be uniformly woven with firm selvedges, the dyeing shall be uniform and shall withstand the dye fastness requirements as stipulated in clause 6.0. The shade of the webbing tapes shall be as per the agreement between buyer and seller.
- 5.2 The webbing shall be woven uniformly and be free from weaving and other manufacturing defects. The selvedges shall be firm and straight. The webbing shall also be free from size or other filling materials and shall not contain any ingredient that is liable to cave subsequent tendering.
- 5.3 It shall be free from objectionable flaws, like missing or broken ends and picks, floats, knots, dyeing defects The web and Tapes shall be clear, free from objectionable matter by which maxistive a fiction weight weight as Buse tending in subsequente stages because the stages are being the stages because the stages are subsequented as a subsequente

CRPF

SL NO.	Webbing of Sling CHARACTERISTICS	REQUIREMENT FOR AK-47 RIFLE	REQUIREMENT FOR CARBINE	METHOD OF TESTS
1	Width(mm)	38÷1	i9+1	IS:(1954)
- 5.	No. of ends in full	G-Láti	G-72	15-19631
	Width	B-30	B-09	
		Ĺ-l	L-1	1
3	Picks per dm.	104	104	-
4.	Tenacity of yarn Gpd. (WEFT)	5.0 (min) 4.5 (min)	5,0 (min) 4.5 (mn)	A
5.	Mass per linear meter g	Sir. Fug	27 +5° u	
б.	Denier of yarn		1	Tablia
	(WARP)	G-1680	G-1680	IS:3442
	Property of the second	B-840	B-840	1
**	(WEFT)	840X2	840X2	1
7.	Colour Fastness	(Rating No.)	(Rating No.) 4 orBetter	18 245
	D. To Light			T.
	ii) To Washing a) Change	4 or Better	4 or Better	1S:764
	in Shade	7012000		1
	b) Staining	4 or Better	4 or Better	
	on on			
	Nivlon			
	iii) Rubbing			i
- 1	a) Dry	4 or Better	4 or Better	IS:766
	b) Wet	4 or Better	4 or Better	
	iv) · Perspiration			
F 2	a)Change in	4 or Better	4 or Better	13:971
	Colour			
0.0	b)Staining on Nylon	4 or Better	4 or Better	
- 8.	pH Value	6.0-8.5	6.0=8.5	IS:1390
9,	Weave	Plain(Basket)	Plain(Basket)	
10.	Nature of fiber	Nylon	Nylon	100

G-Ground end , B- Sinding end , L-Locking end

Slight alteration in the weave design / construction particulars is permissible with the prior approval of AHSP.

iii) BSF Locking tigread of suitable denier shall be uses



7. MARKING

7.1 Each Sling/Belt shall be suitably marked on its inner side with indelibly marking ink/paint showing the contractors name, trade mark, year of manufacture, with cat no (if any) & nomenclature of the store.

8. PRE INSPECTION

8.1 Before tendering the store to the Govt. Inspector, the supplier will carry out thorough pre-inspection of each delivery to satisfy himself that the store fully conform to this specification.

9. PRELIMINARY VISUAL EXAMINATION OF LOT

- 9.1 Before drawing bulk supply sample for laboratory tests the lot shall be examined for visual defects.
- 9.2 The store when visually examined shall be free from weaving and processing flaws.


10. BULK INSPECTION/SAMPLING AND CRITERIA FOR CONFORMITY

- 10.1 The quantity of store offered against one dispatch note shall constitute a lot
- 10.2 The number of web (Sling) to be selected at random for laboratory tests shall be in conformity with the table given below:-

No. of samples to be selected for

Lot size/ No of Slings	Non destructive test(Visual)	destructive test
Up to 10 .	5	2
11 to 30	10	2
31 to 50	15	3
51 to 100	20	4
101 to 500	30	5
501 to 1200	80	5
1201 to 3200	125	- m
3200 to 10,000 & cabove	200	
AND CISE	ITBP SSB NSG	A/Riffe BRP&D

CRPF



- All samples when tested for physical and chemical tests as per relevant specification 10.3 shall conform to the stipulated standards
- The conformity of a lot to the requirements of the standard shall be determined 10.4 on the basis of tests carried out on the sample selected from the lot.
- If, on examination, material from any portion of the consignment found not fully in accordance with this specification, the whole supply is liable to be rejected.

PACKING 11.

- Min 10 No. of the Sling/Belt shall be packed in PP Film of 0.05mm thickness, 1.1 conforming to IS:2508 in neat and dry condition.
- Before dispatch each pack shall be legibly marked with indelible marking 11.2 ink paint showing the following details :-
- Nomenclature and cat. No. of the store
- Quantity packed 11)
- Lot and serial No. iii)
- Month and year of packing iv)
- Name and trade mark of the manufacturer VI
- Name and address of the consignee vi)
- Inspection Note No. and date vii)
- A/T No. and date viii)

WARRANTY CLAUSE 12.

The store supplied against an order shall be deemed to bear a warranty of the contractor against defective materials/workmanship and performance for a period of 6 months from the date of receipt of the stores at consignees depot. If during theies period the stores supplied are found to be defective in any respect by the consignee. the same shall be replaced immediately by the contractor with serviceable stores without any charges or cost.

DATE:

KANPUR STATION:

DEFENCE MATERIALS & STORES RESEARCH & DEVELOPMENT ESTABLISHMENT

DMSRDE POST OFFICE

KANPUR-208-01



